

AguaShield

Water Repellant Admix for Stucco and Mortar



Packaging

1 lb (0.5kg) package

Storage

- Store bags in a cool place, dry location
- 2. Do not store in direct contact with the ground and/or concrete
- 3. Store out of direct sunlight
- 4. Protect containers from weather and other damage.

Shelf Life

2 years

Color White

Product Description

quaShield is a powdered admixture designed to increase the water-resistance of ColorTek Stucco, mortar, or other approved cementitious products. AquaShield is added during mixing and offers the benefit of long-lasting water-resistance, improved stain resistance, and reduced efflorescence without the extra time and expense of applying a sealer.

Features	Benefits
Water-Resistant	Improved freeze/thaw resistance; less efflorescence and staining
Integral	Water-resistance throughout the thickness of the product, unlike surface sealers
Natural Appearance	Does not affect the color or appearance of the finish
Easy to Clean	Helps finish to resist dirt accumulation and allows for easy cleaning
Vapor Permeable	Allows wall to naturally breath which aids drying and helps to prevent mold
Easy to Use	Simply add during mixing; no additional sealers required

Basic Uses

AquaShield is designed as an admix to improve water repellent properties in ColorTek Stucco, mortar, and other cement-based products.

Area of Use

AquaShield may be added to the following products:

- 1. ColorTek Stucco
- 2. Mortar
- 3. Other approved cement-based products

SEP 2016

Application Instructions



Mixing

For use in ColorTek Stucco:

Refer to the appropriate ColorTek product data sheet for additional application and mixing information.

- 1. Add the mix water, ColorPak (if needed), and ColorTek to the mixer per the product data sheet(s).
- 2. After approximately 10 minutes of mixing the ColorTek, add a 1lb (0.45 kg) package of AquaShield into the mix per 90lb (40.8 kg) bag of ColorTek.
- 3. Allow the material to mix for a minimum of 5 additional minutes.
- 4. Turn mixer off and allow the material to take its initial set.
- 5. Retemper the material, adding only enough water to reach the desired consistency.
- 6. Do not over mix.

NOTE: If OmegaCoat is applied to stucco previously treated with Omega AquaShield then replace 1 gallon of the mixing water with 1 gallon of OmegaSeal 1000 per 25-lb bag of OmegaCoat. Refer to the OmegaCoat Product Data Sheet for additional application information.

For use in mortar:

Refer to the manufacturer's product data sheet and/or local code for additional application and mixing information.

- 1. Add the mix water and mortar to the mixer per manufacturer's and/or local code requirements.
- 2. After approximately 3 to 5 minutes of mixing, add a 1lb (0.45 kg) package of AquaShield into the mix per 94lb (42.6 kg) bag of mortar.
- 3. Allow the material to mix for a minimum of 5 additional minutes.
- 4. Turn mixer off and allow the material to take its initial set.
- 5. After approximately 5 to 10 minutes, break the set.

Contact Omega Products for use in other products.

Limitations

DO NOT apply at temperatures below 40°F (4°C) or above 90°F (32°C). Avoid freezing until the material is dry.

DO NOT use below grade.

DO NOT add any other material to the mixture of the product without written approval from Omega Products International.

DO NOT deviate in the mixing or application procedures contained in this, or any other Omega Products Data Sheets, without written approval from Omega Products International.

Cleaning

Cleaning may be accomplished with water and detergent immediately after

KEEP OUT OF REACH OF CHILDREN

www.omega-products.com

and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that

Omega Products International [Manufacturer]
MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE
WITH RESPECT TO THE PRODUCT(S) SOLD
HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer

the best knowledge available to Manufacturer

and can be suggestions.

Technical Assistance

Technical assistance and information is avail
Technical assistance and information is avail
Technical assistance and information is availany claims for infringement of patents result-ing from use of the product. Under no circum-stance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the the buyer's sole and exclusive remedy for any claimed defective product against Manufac-shall determine the suitability of the product.

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect.

to pay Omega's reasonable charges, including The following is made in lieu of all expressed

Technical assistance and information is available by calling Omega Products International at (800) 600-6634 or FAX (951) 520-2594 or by e-mail at info@omega-products.com.

and implied rights, warranties and conditions statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the manufacturer's and is accompanied with proof of pure and batch number.