

MEMBER ASSOCIATIONS

ARIZONA ASSOCIATION
OF WALLS & CEILINGS
602.802.0602

ASSOCIATED PLASTERING
& LATHING CONTRACTORS
619.464.7681

CA-NV CEMENT ASSOCIATION
714.694.0800
WWW.CNCP.CORG

CHICAGO PLASTERING
INSTITUTE
708.371.3100

INTERNATIONAL INSTITUTE
FOR LATH & PLASTER
760.837.9094
WWW.IILP.ORG

LATH & PLASTER CONTRACTORS
ASSOCIATION OF
SAN FRANCISCO/SAN MATEO
650.637.3364
WWW.LATH-PLASTER.ORG

LATH & PLASTERING INSTITUTE
925.283.5160
WWW.IILP.ORG

NORTHWEST WALL & CEILING
BUREAU
800.524.4215
WWW.NWCB.ORG

PLASTERING CONTRACTORS
ASSOCIATION OF
SOUTHERN CALIFORNIA
949.640.9902
WWW.PLASTERINGCONTRACTORS.ORG

PORTLAND CEMENT
ASSOCIATION
847.966.6200
WWW.CEMENT.ORG

RESIDENTIAL PLASTERERS
OF CALIFORNIA
310.523.2088 x2008
WWW.RPAC.BIZ

SACRAMENTO VALLEY BUREAU
FOR LATH & PLASTER
916.444.2397
WWW.CLPCABUREAU.ORG

STUCCO MANUFACTURERS
ASSOCIATION
949.640.9902
WWW.STUCCOMFGASSOC.COM

TECHNICAL SERVICES
INFORMATION BUREAU
714.221.5530
WWW.TSIB.ORG

TEXAS LATHING &
PLASTERING CONTRACTORS
817.461.0676
WWW.TLPCA.ORG

Recommendations For Smooth Troweled Stucco Finishes

Cementitious stucco products, commonly known as Santa Barbara Mission Finish, Santa Barbara Finish, and Smooth Coat, can achieve a range of smooth and semi-smooth finishes. These products were designed to create an old-world finish reminiscent of the early California missions and other early types of plasters. The look of these products is striking, with its natural variation of color and subtle texture profile. These products are especially popular today in European-inspired architectural styles, but can also achieve more contemporary looks through the use of different application techniques.

Smooth stucco products can achieve a natural hand-applied appearance over a properly prepared brown coat substrate. The result will have a natural variation of color and texture, and small cracks from the curing process and normal building movement. Common smooth troweled finish cracking patterns include thin checking in a jagged spider-web pattern and stress cracks emanating from corners of doors and windows. Natural color variations occur, because the act of troweling stucco to a smooth finish causes “burn” marks, where the color is accentuated and darkened. Note that “burn marks” are by their nature inconsistent, and should not be expected to be consistent in color or frequency across an entire building. Small pigment streaks can also occur depending on color and load of pigment. Typically, smooth troweled finishes are troweled on in two thin coats.

By following a few industry best practices, the occurrence of cracking in smooth troweled finishes can be reduced. The use of control joints, adherence to manufacturers’ recommendations for curing, and scheduling final plastering after sources of building stress are reduced can all minimize excessive cracking. For instance, roofs should be fully loaded, interior drywall should be installed, and the brown coat should be given at least seven days to cure (14 days is recommended) to find its equilibrium prior to the application of the finish coat of plaster.

Stucco finishes should not be expected to produce perfection, particularly with a smooth plaster finish. Refer to member associations, manufacturers, or plastering contractors for recommendations for alternative materials and methods to minimize cracking and enhance the overall performance of the plaster finish.

MAY 2008